

परिशिष्ट-1

कार्यालय कार्यपालन यंत्री लोक निर्माण विभाग सम्भाग मुरैना (म0प्र0)
 क्रमांक.....526./लेखा/2018-19 मुरैना दिनांक..11-2-2019
 प्रति,


कलेक्टर

जिला मुरैना(म0प्र0)

विषय:-चम्बल नदी पर निर्माणाधीन उसैदघाट पुल के निर्माण में उपयोग हो रही रेत की गुणवत्ता के सम्बन्ध में ।

.....00000.....
 उपरोक्त विषयान्तर्गत लेख है कि विगत माह सडक निर्माण कार्यों की मीटिंग के दौरान दिये गये निर्देशों के पालन में उसैदघाट पुल निर्माण में उपयोग में लाई जा रही रेत का स्थल पर आकस्मिक तौर पर निरीक्षण के दौरान सिन्ध नदी का रेत उपयोग होना पाया गया था जिसके स्थल से सेम्पल एकत्रित कर क्षेत्रीय अनुसंधान परीक्षण प्रयोगशाला ग्वालियर को सीलड कर परीक्षण हेतु भेजे गये थे । प्रयोगशाला से प्राप्त परीक्षण परिणाम के अनुसार पुल के निर्माण में उपयोग की जाने वाली रेत Grade-1 Type की होना पाई गई है, जिसका Finess modulus 3.19 है इस प्रकार निर्माण कार्य में उपयोग लाया जा रहा रेत मानक रूप है । परिणामों की छायाप्रति सूचनार्थ प्रेषित ।

सहपत्र:-परीक्षण परिणाम की छायाप्रति


 कार्यपालन यंत्री
 लोक निर्माण विभाग सम्भाग मुरैना

**ZONAL RESEARCH LABORATORY
MP P.W.D. (NORTH ZONE), THATIPUR -GWALIOR**

No. ZRL/Lab No 23/01-2019 / 22.....

Gwalior, Dated: 18/01/2019

To.

Executive Engineer,
P.W.D. Division. Morena.

Sub: Test report(s) of Construction Material.


Ref: Your Letter No/173/लेखा/2018-19

Morena, Dated : 14/01/2019

Kindly find enclosed here with Witness Certificate and Test Report (s) of your sample (s) as received in this laboratory vide reference cited above for your information and necessary action.

Encl:

- (i) Witness Certificate (1)
- (ii) Test report -One Sheet


Assistant Engineer
In Charge
Zonal research Laboratory
M.P. P.W.D. (North Zone) Gwalior

ZONAL RESEARCH LABORATORY MP P.W.D. (NORTH ZONE), THATIPUR GWALIOR

RESULT SHEET (TESTS OF FINE AGGREGATE / SAND)

Lab No 23/01-2019

Date of Testing: 17-18/01/2019

- 1- Type of sample* : Sand
2- Authority : Executive Engineer, P.W.D., Division, Morena
3- Reference No : No/173/लेखा/2018-19 Morena, Dated : 14/01/2019
4- Name of work* : चम्बल नदी के उसैदघाट पुल पर उपयोग हो रहे रेत का परीक्षण।
5- Conditions of Sample as received in Lab. : Sealed#
6- Testing Charge : Rs 800/- Vide Challan No.- 20
Dated-15/01/2019 SBI Branch.-Moti Mahal, Gwalior.

TESTS OF FINE AGGREGATE / SAND

S.No	Identification of Sample	Silt & Clay Content in %	Fineness Modulus	Gradation						
				% Weight passing through I.S. sieve size						
				10 mm	4.75 mm	2.36 mm	1.18 mm	600 Micron	300 Micron	150 Micron
1	Not Provided / Lab No. 23/01-2019	03.33	03.19	100	97.42	82.56	58.53	32.25	08.16	01.38

These results are confirmed and confined to samples as received as in this Laboratory only.
*As inform by concerning.
Properly sealed sample through official person are expected for reliability of sample & results.

Test Perform by

Laboratory Assistant

Countersigned